



PEXIDAN[®] U/T

**Low density moisture curable polyethylene compound
for low voltage underground service entrance cables
(UL styles USE and USE-2).**

Description

Pexidan® U/T is a low density XLPE System curable by moisture and consists of a silane pre-grafted base compound A-3001 and a catalyst masterbatch CAT-008. When mixed and extruded in the proper proportions (95/5), the two components result in a material curable by exposure to 70-90°C hot water or even ambient moisture. In order to prevent pre-scorching the grafted compound and the catalyst masterbatch must be stored separately and mixed only when used.

Physical and mechanical properties	typical value	unit	test method
- Specific gravity at 23°C	0.92	g/cm3	ASTM D-792
- MFR, 190°C/2,16 kg	0.8	g/10'	ASTM D-1238
- Mechanical properties: tensile strength at break tensile strength at yield elongation at break	2200 1800 450	psi psi %	UL 1581
- Mechanical Properties: after thermal ageing (7d @ 121°C): Tensile strength at break Elongation at break After 60 day oil @ 75°C Tensile strength at break Elongation at break After 30 day gasoline @ 23°C Tensile strength @ break Elongation @ break	1950 350 1850 330 1825 350	psi % psi % psi %	UL 1581
- Weatherometer testing (300 hr. exposure) Original tensile strength After exposure Original elongation After exposure	2650 2870 440 430	psi psi % %	UL 1581
- Deformation	1	%	UL 1581
- Hot set test, 15 minutes @ 150°C elongation under load	40	%	IEC 811
- Crushing test	1400	lbs	UL 1581
- Dielectric Breakdown after glancing impact	35 33	kV	UL 1581
- Degree of Crosslinking	72	%	ASTM D-2765
- Insulation Resistance @23°C @90°C after 12 weeks @90°C	560,000 21,000 50,000	MΩ/1000 ft.	UL 1581

Typical values reported above (except MFR and Weatherometer) are obtained from 14 AWG samples with 30-mil wall thickness, cured in hot water (6 hours @ 95°C). Weatherometer testing was performed on 7 stranded, 6 AWG sample.

Processing

The pregrafted base Pexidan® A-3001 must be added with type CAT-008 catalyst masterbatch in the proportion 95:5 by weight. Mixing must be done just before consumption; we suggest dosing the two components directly in the hopper of the extruder using a proper mixing device. Pexidan® U/T can be processed with PE single screw extruders having proper temperature control and a good mixing screw (2.5:1 ratio at least).

The following temperature profile is suggested:

barrel zones:	from 310 to 340 °F
head:	365 °F
die:	365 °F
screw:	neutral

These conditions may depend on the equipment being used. It is recommended using conveyors and tools shaped in order to prevent stagnation in the head. In case of prolonged shutdown, purge the extruder with LDPE.

Curing can be done in the following ways:

- by immersion in hot water at 70-90°C
- by exposure to low pressure steam
- ambient atmospheric moisture

In all cases curing time depends on wall thickness, temperature, relative humidity and quantity of wire on the reel.

A wide range of commonly used color masterbatches based on LDPE are available. A use level of 1.5% by weight should give an acceptable color but this will be dependent upon the concentrate itself. Levels of concentrates should be kept to a minimum because they can detract from performance. It is recommended that the catalyst and colour masterbatches be dried prior to usage 4-6 hours at 60°C (150°F) using a desiccant dryer.

Storage

Due to the moisture sensitivity of Pexidan® Padanaplast USA suggests that the following points should be considered when storing the materials:

- Ambient temperature generally not exceeding 30°C
- Avoid direct exposure to sunlight and weathering
- Once the package has been opened it is suggested that the entire contents be used.

Packaging

The physical form of both Pexidan® A-3001 and CAT-008 is free-flowing pellets, and are available in 1500 lb (680 kg) gaylords, or in 300 lb (145 kg) fibre drums.

Our Technical Service is at your disposal for further information and assistance.

The technical information contained herein is, to the best of our knowledge, believed to be accurate. However, Padanaplast USA, makes no guarantee or warranty, and does not assume any liability, with respect to the accuracy or completeness of such information. Suitability of material for a specific final end use is the sole responsibility of the user. The data contained herein are typical properties only and are not to be used as specifications.



Padanaplast USA Inc.

3220 Crocker Avenue, Sheboygan, WI 53081
Phone 920-803-0778. Fax 920-803-0779
www.padanaplastusa.com